

TEROSON® MS 9360 2C

September 2023

Product description

TEROSON® MS 9360 2C provides the following product characteristics:

Technology	Silane-modified polymer
Product type	Adhesive/Sealant
Components	Two-component
Cure	Cure at ambient temperature
Appearance (Component A)	Black
Appearance (Component B)	White
Consistency	Pasty, Thixotropic
Odor	Characteristic
Mix ratio, by volume (Component A : B)	10:1

TEROSON® MS 9360 2C is a high viscous, flame resistant, two-component adhesive based on silane modified polymers which cures to an elastic product. The material is free of solvents, isocyanates and silicones. After component A has been thoroughly mixed with component B the curing starts - independent of humidity - to form an elastic material. In order to really make use of the advantage of elastic bonding, care should be taken of a sufficient dimensioning of the bonding joint. A minimum thickness is necessary so that the elastic adhesive is able to compensate the movements between the materials to be bonded under the influence of different temperatures during final use of the bonded part.

Application areas:

TEROSON® MS 9360 2C is used in the automotive industry for elastic bonding and sealing applications.

Technical data

Component A, density, g/cm ³	approx. 1.4
Component B, density, g/cm ³	approx. 1.3
Mixture (Component A+B)	
Sag resistance	no sagging
Pot life, min*	ca. 5
Shore-A-hardness, ISO 868, Durometer A	ca. 55
Tensile strength, ISO 37, MPa	ca. 3.4
Elongation at break, acc. to ISO 37, speed 200 mm/min, %	ca. 200
Tensile shear strength (acc.to EN 1465, speed 10 mm/min), MPa	ca. 2.5
Application temperature, °C	5 to 40
In service temperature range, °C	-40 to 100
Short-term (up to 1 hr), °C	120
* ISO 291 standard climate	23°C, 50%, relative air humidity
Flame resistance, UL 94	HB

Direction for use

Preliminary statement:

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Pre-Treatment:

The substrates must be clean, dry, oil- and grease free. Cleaners Teroson PU 8550 or Teroson VR 10 are recommended for this. Depending on the surface it can be necessary to roughen the surface or to use an adhesion promoter e.g. Teroson PU 8517 H or Teroson SB 450 to provide best adhesion. When manufacturing plastics, external release agents are often used; these agents must be accurately removed first. Due to the different compositions of paints, especially powderpaints and the large number of different substrates, application trials before use are necessary.

Application:

TEROSON® MS 9360 2C consists of components A and B. A and B components are applied with suitable application guns or automated equipment in a volume ratio of 10:1 and homogeneously mixed with a static mixer shortly before application. Low material temperatures of the sealant lead to an increase in viscosity, which is noticeable through a reduced squeeze-out rate.

Classification:

Please refer to the corresponding **Material Safety Data Sheets** for details on:

Hazardous Information
Transport Regulations
Safety Regulations

Storage:

Frost-sensitive	no
Recommended storage temperature, °C	10 to 25
Shelf-life (in unopened original packaging), months	12

Additional information

Disclaimer

The information provided in this Technical Data Sheet (TDS) including these recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage:

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1

Henkel AG & Co. KGaA
40191 Düsseldorf, Germany
Phone: +49-211-797-0

Henkel Corporation USA
Madison Heights, MI 48071
Phone: +1-248-583-9300

Henkel (China) Co. Ltd.
201203 Shanghai, China
Phone: +86.21.2891.8000